

KOSMO FOTO AGENT SHADOW DEVELOPING TIMES

DEVELOPER	DILUTION	ISO	TIME (MINS)	TEMP (°C)	TEMP (°F)
510 Pyro	1+100	400	11	20	68
510 Pyro	1+100	1600	25	20	68
Acufine	1+3	400	10	28	82
Acufine	1+3	640	10	28	82
D-76	Stock	400	9.5	20	68
D-76	1+1	400	14	20	68
D-76	Stock	800	12.5	20	68
D-76	Stock	1000	14.5	20	68
D-76	Stock	1600	20	20	68
D-76	1+1	1600	22	20	68
HC-110	B	400	5-6	20	68
HC-110	E	400	8-9	20	68
HC-110	E	800	13	20	68
ID-11	Stock	400	9.5	20	68
ID-11	1+1	400	16.5	20	68
ID-11	Stock	800	13	20	68
ID-11	Stock	1000	14.5	20	68
ID-11	Stock	1600	20	20	68
Ilfosol 3	1+9	400	6.5	20	68
Ilfosol 3	1+14	400	11	20	68
Ilfosol 3	1+9	800	15	20	68
Ilfosol 3	1+14	800	25	20	68
Ilfosol 3	1+19	1600	27	18	65
Ilfotec DD-X	1+4	400	11.5	20	68
Ilfotec DD-X	1+9	400	40	24	75
Ilfotec DD-X	1+4	800	13	20	68
Ilfotec DD-X	1+4	1600	17	20	68
Microphen	Stock	400	8	20	68
Microphen	1+1	400	15	20	68
Microphen	Stock	800	10	20	68
Microphen	1+1	800	19	20	68
Perceptol	Stock	400	10	20	68
Rodinal	1+25	400	7.5	20	68
Rodinal	1+50	400	20	20	68
Rodinal	1+25	800	9	20	68
Rodinal	1+25	1600	25	20	68
TMax Dev	1+4	400	5.5	20	68
TMax Dev	1+9	400	10	20	68
TMax Dev	1+9	1600	18	20	68
XT-3	Stock	400	9	20	68
XT-3	1+1	400	12	20	68
XT-3	1+2	400	15	20	68

	XT-3	Stock	800	10.5	20	68	
	XT-3	1+1	800	14.5	20	68	
	XT-3	1+1	1600	13	20	68	
	XT-3	Stock	3200	17.5	20	68	
	XT-3	Stock	6400	21	20	68	
	Xtol	Stock	400	9	20	68	
	Xtol	1+3	400	18	20	68	
	Xtol	Stock	800	10.5	20	68	
	Xtol	1+1	800	14.5	20	68	
	Xtol	Stock	1600	13	20	68	
	Xtol	1+1	1600	18	20	68	
	Xtol	Stock	3200	17.5	20	68	
	Xtol	Stock	6400	21	20	68	
	If you have recommendations of your own, please let us know via foto.dowling@gmail.com.						
	It would be great to add to this list with example pictures which could help people						
	choose developers based on the look they desire.						